

**Product / brand:** Eural EcoPro

**Paper Mill:** Le Bourray

**Country of origin:** France

**Website:** [www.arjowigginsgraphic.com](http://www.arjowigginsgraphic.com)

## eural ecoPro

### Product Data

---

Eural is a range of high quality natural white 100% recycled papers, manufactured at the Papeteries du Bourray Mill in Le Mans, France. Eural is manufactured using de-inked post-consumer and post-industrial waste (the de-inked pulp is produced on site) without any bleaching processes.

Eural EcoPro offers outstanding qualities including excellent opacity, a smooth finish and great printability.

**Naturally, Eural's services live up to your expectations.**

- Eural EcoPro is a 100% recycled matt coated paper with a natural whiteness
- Eural EcoPro is available in the following weights: 70, 80, 90, 100, 115, 130, 150 and 170 gsm

*For more in-depth environmental information, please request the Environmental Declaration or visit [www.arjowigginsgraphic.com](http://www.arjowigginsgraphic.com)*

### Certified Management Systems & Product certifications

---

*For more in-depth environmental information, please request the Environmental Declaration or visit [www.arjowigginsgraphic.com](http://www.arjowigginsgraphic.com)*

- ISO 9001 (Quality Management Standard)
- ISO 14001 (Environmental Management Standard)
- OHSAS 18001 (Health and Safety Management System)
- EU Ecolabel (n°FR/011/003)
- Blue Angel
- Paper By Nature
- Association des Producteurs et Utilisateurs de Papiers Recycles (APUR)
- National Association of Paper Merchants (NAPM)
- DIN 6738 Permanent Paper Standard
- FSC® Certified available on request

### Applications

---

Suitable for a range of applications (depending on grammage):

Manuals, brochures, inserts, financial reports, invitations, catalogues, school exercise books, calendars, dividers, press kits, etc.

For use in exercise books, a specific treatment can be added on request.

### Recommendations

---

**Printing processes:**

- Sheet fed offset, silkscreen.
- Printing inks : all inks suitable for coated paper
- Suitable for laser and inkjet personalisation
- Recommended frame = 150 to 175.
- Recommended wet pH = 5,5.

**Converting:**

- Suitable for gumming, sealing, perforation, film deposit, varnishing
- Folding (pre-creasing is recommended for 150gsm and above)

## Technical specification

---

If you seek information not shown below, contact your local sales office, email [graphic@arjowiggins.com](mailto:graphic@arjowiggins.com) or visit [www.arjowigginsgraphic.com](http://www.arjowigginsgraphic.com)

EURAL ECOPRO					
	ISO 534	ISO 11475	ISO 2471	ISO 5627	ISO 8254
Weight (gsm)	Bulk (cm <sup>3</sup> g)	CIE Whiteness (%)	Opacity (%)	Smoothness	Gloss (%)
70	0.97	87	92	110-180	15-25
80	0.95	87	93	110-180	20-30
90	0.95	87	94	110-180	20-30
100	0.90	87	95	110-180	20-30
115	0.90	87	96	110-180	20-30
130	0.90	87	97	110-180	20-30
150	0.90	87	98	110-180	20-30
170	0.90	87	98	110-180	20-30