

Product / brand: Maine 1 Face green

Paper Mill: Wizernes

Country of origin: France

Website: www.arjowigginsgraphic.com

MAINE 1 FACE GREEN

Product Data

Maine 1 Face Green is the only one-side coated recycled stock available to the packaging paper market combining 60% FSC® certified recycled pulp and 40% FSC virgin fibre pulp. Maine 1 Face Green provides the same technical and aesthetic quality standards as virgin fibre-based one-side coated paper but offers real and immediate environmental benefits to businesses.

- Maine 1 Face Green is used for labelling, thermo-bonding and flexible packaging.

Maine 1 Face Green is available in the following grammages: 80, 85, 90, 100, 110, 120, 135 and 150 gsm

Certified Management Systems & Product certifications

For more in-depth environmental information, please request the Environmental Declaration or visit www.arjowigginsgraphic.com

- ISO 9001 (Quality Management Standard)
- ISO 14001 (Environmental Management Standard)
- OHSAS 18001 (Health and Safety Management System)
- National Association of Paper Merchants (NAPM)
- FSC® certified (No. FSC-C021878)
- Food contact compliance
- EU Ecolabel (No. SGS-COC-003161)
- HP Indigo certified

Applications

Suitable for a range of applications (depending on grammage):

- Labels for cans, glass or plastic containers.
- Lamination for luxury and fragrance packaging, games boxes and puzzles.
- Soft packaging: coffee, chocolate, cigarettes.

Recommendations

Printing processes:

- Sheet and reel fed litho, flexo, screen (certain grammages).

Converting:

Can be laminated with aluminium, is suitable for PE coating, film coating, hot melt applications and various types of glue and varnish.

Technical specification

If you seek information not shown below, contact your local sales office, email graphic@arjowiggins.com or visit www.arjowigginsgraphic.com

MAINE 1 FACE GREEN							
	ISO 534	ISO 11475	ISO 2471	ISO 5629	ISO 5629	TAPPI / ISO???	ISO 5627
Weight (gsm)	Bulk (cm ³ /g)	CIE Whiteness (%)	Opacity (%)	Dynamic stiffness MD (mN.m)	Dynamic stiffness CD (mN.m)	Gloss (%)	Beck Smoothness V ^o
80	0.81	118	88	11	6	66	800
85	0.81	118	89	13	7	67	700
90	0.80	118	89	14	9	67	880
100	0.81	118	91	20	12	68	900
110	0.80	118	93	24	15	68	750
120	0.80	118	94	31	19	70	750
135	0.80	118	96	42	27	70	700
150	0.81	118	97	59	38	70	580